



Advance Industrial

毅華實業

Item Number – M-ST2744

Usage in Karat¹

14K – 18K

Colour White

Commercial Composition CU 57%, NI 15%, AG 10%, ZN 18%

Properties

Hardness

150 (Hv)

Density

13 (gm/cm³)

Handcraft, Wire Drawing, Sheet Rolling, Stamping

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com