



Advance Industrial

毅華實業

Item Number – M5167

Usage in Karat¹	14K	Colour	Green Yellow
Commercial Composition	AG 84%, CU 13%, ZN 3%		

Properties

Hardness	118 (Hv)
Density	12.8 (gm/cm ³)
Flask Temperature²	640°C - 660°C
Casting Temperature²	1020°C - 1040°C
Cool Down Time	30 Minutes
Casting Parameters	Vacuum Pressure Casting / Manual Vacuum Casting

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com