



Advance Industrial 毅華實業

Item Number – M7131B

Usage in Karat¹	18K	Colour	Yellow
Commercial Composition	CU 45%, AG 35%, ZN 20%		

Properties

Hardness	125 (Hv)
Density	14.8 (gm/cm ³)
Flask Temperature²	670°C - 700°C
Casting Temperature²	1030°C - 1050°C
Cool Down Time	30 Minutes
Casting Parameters	Vacuum Pressure Casting / Manual Vacuum Casting

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com