



Advance Industrial 毅華實業

Item Number – M-ST3070NF

Usage in Karat¹

9K – 10K

Colour White

Commercial Composition AG 80%, ZN 16%, CU 4%

Properties

Hardness

125 (Hv)

Density

11 (gm/cm³)

Handcraft, Wire Drawing, Sheet Rolling, Stamping

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com