



Advance Industrial

毅華實業

Item Number – LA20

Usage in Karat¹	AG925	Colour	Silver White
Commercial Composition	CU 58%, ZN 42%		

Properties

Hardness	90 (Hv)
Density	10.3 (gm/cm ³)
Flask Temperature	630°C - 660°C
Melting Temperature²	980°C - 1000°C
Cool Down Time	30 Minutes
Casting Parameters	Vacuum Pressure Casting / Manual Vacuum Casting

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com