



Advance Industrial

毅華實業

Item Number – M-ST7345

Usage in Karat¹

18K

Colour Yellow

Commercial Composition AG 49%, CU 45%, ZN 6%

Properties

Hardness

125 (Hv)

Density

14.8 (gm/cm³)

Handcraft, Wire Drawing, Sheet Rolling, Stamping

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com