



Advance Industrial

毅華實業

Item Number – D32P

Usage in Karat¹	18K	Colour	White
Commercial Composition	AG 56%, PD 32%, ZN 7%, CU 5%		

Properties

Hardness	130 (Hv)
Density	14.6 (gm/cm ³)
Flask Temperature²	670°C - 700°C
Casting Temperature²	1030°C - 1050°C
Cool Down Time	30 Minutes
Casting Parameters	Vacuum Pressure Casting / Manual Vacuum Casting

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com