



Advance Industrial 毅華實業

Item Number – M-ST7338

Usage in Karat¹	18K	Colour	Red
Commercial Composition	CU 92%, AG 4%, ZN 4%		

Properties

Hardness	140 (Hv)
Density	14 (gm/cm ³)
	Handcraft, Wire Drawing, Sheet Rolling, Stamping

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com