



# Advance Industrial

## 毅華實業

**Item Number – M-ST1666**

**Usage in Karat<sup>1</sup>**

10K – 14K

**Colour** Yellow

**Commercial Composition** CU 70%, ZN 19%, AG 11%

---

## Properties

**Hardness**

125 (Hv)

**Density**

13.6 (gm/cm<sup>3</sup>)

Handcraft, Wire Drawing, Sheet Rolling, Stamping

<sup>1</sup>When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

<sup>2</sup>Depending on the thickness of the product, select the appropriate flask temperature

**WeChat (HK)**



**WeChat (China)**



**WhatsApp**



[www.advanceindustrial.com](http://www.advanceindustrial.com)



[info@advance-industrial.com](mailto:info@advance-industrial.com)