



Advance Industrial

毅華實業

Item Number – M5123I

Usage in Karat¹	9K – 14K	Colour	Light Yellow
Commercial Composition	CU 63%, AG 20%, ZN 17%		

Properties

Hardness	120 (Hv)
Density	12.5 (gm/cm ³)
Flask Temperature²	640°C - 660°C
Casting Temperature²	1020°C - 1040°C
Cool Down Time	30 Minutes
Casting Parameters	Vacuum Pressure Casting / Manual Vacuum Casting

¹When melting alloys, inert gases or unsaturated oxygen flames should be used to protect the alloy and prevent oxidation of the alloy

²Depending on the thickness of the product, select the appropriate flask temperature

WeChat (HK)



WeChat (China)



WhatsApp



www.advanceindustrial.com



info@advance-industrial.com